

READ THESE MIXING INSTRUCTIONS FIRST

IMPACT 100% EPOXY

READ THESE MIXING INSTRUCTIONS FIRST

ALL of Part-B container must be mixed with the Part-A container.
Pour the entire contents of Part-B into Part-A.

DO NOT SEPARATE PART-A OR PART-B INTO SMALLER KITS

Impact 100% Epoxy Coating should be applied only on clean sound surfaces free from oil, grease, dust, dirt and wax. Also, do not apply coating over paint subject to flaking or any other foreign matter.

- Clean all concrete surfaces with a solution of Industrial Cleaner and Degreaser, then rinse thoroughly.
- Once the surface has been cleaned, allow to dry for 24 hours before you can apply the coating.
- If you are painting over a previously painted surface, be sure to roughen the surface with sandpaper, then clean. If you clean this surface with water, allow to dry 24 hours before applying the coating.

It is our recommendation that you remove any existing paint from the surface before you apply Impact 100% Epoxy for maximum adhesion.

- **Do not mix Part-A and Part-B until you are ready to begin application.**
- **Do not tint product to change color.**
- **When mixed, product has a 1 hour pot life.**

Pour entire contents of Part-B into container of Part-A. Mix product thoroughly for at least 3 minutes with the hand paddle. Be sure to scrape the sides and bottom of the pail to ensure complete mixing. If not mixed properly, coating will take longer to dry or may not dry at all.

Apply the coating with a brush or lint free low pile roller. If applying a second coat, allow first coat to dry for 16 hours.

DO NOT SEPARATE PART-A OR PART-B TO MAKE SMALLER KITS